

D10 – D18

DEUTSCH

Zusammensetzung

Grundgewebe 75% PES, 20% CO,
5% CV

Nutzschicht 100% PU

Gewicht

393 g/m² (+/- 5%)

Scheuerfestigkeit

> 100.000 Touren

Lichtechtheit

Note > 5

Reibechtheit

Nass 5, Trocken 4

ENGLISH

Composition

base 75% PES, 20% CO, 5% CV
surface 100% PU

Weight

393 g/m² (+/- 5%)

Abrasion resistance

> 100.000 cycles

Lightfastness

Note > 5

Rubfastness

wet 5, dry 4

FRANÇAIS

Composition

base 75% PES, 20% CO, 5% CV
couche supérieure 100% PU

Poids

393 g/m² (+/- 5%)

Résistance à l'abrasion

> 100.000 tours

Résistance à la lumière

Note > 5

Résistance au frottement

mouillé 5, sec 4

ITALIANO

Composizione

composizione di base 75% PES,
20% CO, 5% CV
composizione superficie 100% PU

Peso

393 g/m² (+/- 5%)

Resistenza all'abrasione

> 100.000 cicli

Solidità alla luce

Note > 5

Resistenza allo sfregamento

bagnato 5, secco 4
